

TABOREN PH 41 G 30

Polypropylene Homopolymer

SILON s.ro

Message:

TABOREN PH 41 G 30 is a Polypropylene Homopolymer (PP Homopolymer) product filled with 30% glass fiber. It is available in Asia Pacific or Europe. Applications of TABOREN PH 41 G 30 include automotive and engineering/industrial parts. Primary characteristic: homopolymer.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Homopolymer		
Uses	Engineering Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	75.0	MPa	ISO 527-2/1B/50
Flexural Modulus	5500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	166	°C	ISO 306/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT