

Visico™ LE4423 / Visico™LE4438

Low Density Polyethylene

Borealis AG

Message:

Visico LE4423 / Visico LE4438 is a silane crosslinkable natural compound designed for low voltage power cables up to 6 kV.

Visico LE4423 and Visico LE4438 is a combination of a Visico base material and a catalyst master batch which accelerates the moisture-induced crosslinking reaction.

When properly mixed, addition of 5 parts of Visico LE4438 to 95 parts of Visico LE4423 , insulation with excellent thermo-oxidative stability, also in contact with copper as well as aluminium, is achieved.

General Information			
Features	Low Density		
Uses	Cable Jacketing		
	Wire & Cable Applications		
	Wire Jacketing		
Agency Ratings	ASTM D 1248, I, Class A, Cat. 4		
	HD 603 S1		
	HD 604 S1		
	IEC 60502-1		
	NEMA WC-70		
	NEMA WC-71		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density ¹	0.923	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance (50°C, 10% Igepal, F20)	> 96.0	hr	IEC 60811-4-1/B
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 1 sec)	52		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	> 15.0	MPa	ISO 527-2/250
Tensile Strain (Break)	> 300	%	ISO 527-2/250
Aging	Nominal Value	Unit	Test Method
Mechanical Properties After Aging in Air Oven, 135°C, 240 hr (Change in Tensile Strength)	< 25	%	IEC 60811
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -76.0	°C	ASTM D746
Hot Set ²			IEC 60811-2-1
Elongation under load : 200°C	60	%	

Permanent deformation : 200°C	0.0	%	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+16	ohms·cm	IEC 60093
Electric Strength	> 22	kV/mm	IEC 60243-1
Dielectric Constant (50 Hz)	< 2.30		IEC 60250
Dissipation Factor (50 Hz)	< 5.0E-4		IEC 60250
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	150	°C	
Cylinder Zone 2 Temp.	170	°C	
Cylinder Zone 3 Temp.	170	°C	
Cylinder Zone 4 Temp.	170	°C	
Die Temperature	170	°C	
NOTE			
1.	Mixture 95:5		
2.	0.20 MPa		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

