PETLIN LD C150Y

Low Density Polyethylene PETLIN (MALAYSIA) SDN BHD

Message:

PETLIN LD C150Y is a low density polyethylene resin for general purpose and film applications. It is produced by the state-of-the-art DSM Stamicarbon tubular process. It contains antioxidant (BHT free), slip and antiblock additives. It is intended primarily for blown film process.

General Information			
Additive	Antioxidant		
	High Antiblock		
	High Slip		
Features	Antioxidant		
	Food Contact Acceptable		
	Good Drawdown		
	Heat Sealable		
	High Antiblocking		
	High Clarity		
	High Gloss		
	High Slip		
	Low Gel		
Uses	Bags		
	Film		
	Foam		
	Laundry Bags		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Blown Film		
	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.921	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction	0.10		ASTM D1894
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	μm	
Film Thickness - Recommended / Available	150 to 60 μm		

Tensile Modulus			ISO 527-3
MD : 25 μm	202	MPa	
TD : 25 μm	224	MPa	
Tensile Stress			ISO 527-3
MD : Break, 25 µm	26.0	MPa	
TD : Break, 25 μm	15.0	MPa	
Tensile Elongation			ISO 527-3
MD : Break, 25 µm	150	%	
TD : Break, 25 μm	610	%	
Dart Drop Impact (25 μm)	86	g	ASTM D1709
Elmendorf Tear Strength			ISO 6383-2
MD : 25 μm	80000	N	
TD : 25 μm	30000	N	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.0 μm)	66		ASTM D2457
Haze (25.0 μm)	6.5	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	145 to 165	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

