

TRIBOCOMP® PA66 TS7

Polyamide 66

EPIC Polymers

Message:

TRIBOCOMP® PA66 TS7 is a polyamide 66 (nylon 66) product. It is available in Europe. The main characteristics are: lubrication.

General Information				
Additive	PTFE + Silicone Lubricant (20%)			
Features	Lubrication			
Forms	Particle			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.25	--	g/cm ³	ISO 1183
Molding Shrinkage - Flow	1.3	--	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	2.5	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	2800	1050	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	65.0	45.0	MPa	ISO 527-2
Tensile Strain (Break)	12	20	%	ISO 527-2
Flexural Modulus (23°C)	2650	900	MPa	ISO 178
Flexural Stress (23°C)	80.0	55.0	MPa	ISO 178
Coefficient of Friction				ASTM D3702
Dynamic	0.10	--		ASTM D3702
Static	0.070	--		ASTM D3702
Wear Factor	8.00	--		ASTM D3702
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	--	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	55	--	kJ/m ²	ISO 179
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	220	--	°C	ISO 75-2/B
1.8 MPa, not annealed	80.0	--	°C	ISO 75-2/A
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+12	--	ohms	ASTM D257
Dielectric Strength (2.00 mm)	30	--	kV/mm	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112
Additional Information				

干燥

The value listed as Molding Shrinkage ISO 294-4, was tested in accordance with S.O.P. methods.

Injection	Dry	Unit
Drying Temperature	80.0	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	270 - 300	°C
Middle Temperature	275 - 295	°C
Front Temperature	270 - 295	°C
Nozzle Temperature	280 - 310	°C
Processing (Melt) Temp	< 300	°C
Mold Temperature	80.0 - 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

