

LEXAN™ 503RS resin

Polycarbonate

SABIC Innovative Plastics Europe

Message:

LEXAN 503RS is a medium viscosity, glass reinforced, flame retardant grade UV stabilized grade.

General Information			
UL YellowCard	E45329-100766660		
Filler / Reinforcement	Glass Fiber		
Additive	UV Stabilizer		
Features	Flame Retardant		
	Medium Viscosity		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.26	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	8.00	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow ¹	0.20 to 0.60	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.31	%	
Equilibrium, 23°C, 50% RH	0.13	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	115	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3900	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/5
Yield	70.0	MPa	
Break	65.0	MPa	
Tensile Strain			ISO 527-2/5
Yield	3.0	%	
Break	4.0	%	
Flexural Modulus ²	4000	MPa	ISO 178
Flexural Stress	120	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³			ISO 179/1eA
-30°C	8.0	kJ/m ²	
23°C	9.0	kJ/m ²	
Charpy Unnotched Impact Strength ⁴			ISO 179/1eU

-30°C	No Break		
23°C	No Break		
Notched Izod Impact Strength ⁵			ISO 180/1A
-30°C	8.0	kJ/m ²	
23°C	9.0	kJ/m ²	
Unnotched Izod Impact Strength ⁶			ISO 180/1U
-30°C	100	kJ/m ²	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁷			
0.45 MPa, Unannealed, 100 mm Span	142	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 100 mm Span	137	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	144	°C	ISO 306/B50
--	147	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE - Flow (23 to 80°C)	4.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.21	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength (3.20 mm, in Oil)	16	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
50 Hz	2.90		
60 Hz	2.90		
1 MHz	2.80		
Dissipation Factor			IEC 60250
50 Hz	1.0E-3		
60 Hz	1.0E-3		
1 MHz	0.010		
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm, Testing by SABIC)	V-0		UL 94
Glow Wire Flammability Index (1.00 mm)	960	°C	IEC 60695-2-12
Oxygen Index	36	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 to 80.0	°C	
Rear Temperature	270 to 300	°C	
Middle Temperature	280 to 310	°C	
Front Temperature	290 to 320	°C	

Nozzle Temperature	280 to 310	°C
Processing (Melt) Temp	290 to 320	°C
Mold Temperature	80.0 to 120	°C

NOTE		
1.	Tensile Bar	
2.	2.0 mm/min	
3.	80*10*3 sp=62mm	
4.	80*10*3 sp=62mm	
5.	80*10*3	
6.	80*10*3	
7.	120*10*4 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT