

Delene 5598

Thermoplastic Elastomer

Shanghai Lin Gen Rubber Materials Co., Ltd.

Message:

Halogen free flame retardant TPE for Wire & Cable applications, with excellent elasticity

General Information			
Features	High elasticity		
	Halogen-free		
	Flame retardancy		
Uses	Wire and cable applications		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	98		ASTM D2240
Shaw D	50		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	15.0	MPa	ASTM D412
Tensile Elongation (Break)	380	%	ASTM D412
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+14	ohms·cm	ASTM D257
Dielectric Strength	> 20	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.0 mm)	V-0		UL 94
Extrusion	Nominal Value	Unit	
Drying Temperature	80 - 90	°C	
Drying Time	3.0 - 4.0	hr	
Extrusion instructions			
Hopper Temperature: 150 - 170 °CTransmission Temperature: 180 - 200 °CMeasurement Temperature: 200 - 230 °CDie Temperature: 190 - 220 °CMesh Temperature: 100 - 200 mesh			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

