

LEXAN™ LUX9610 resin

Polycarbonate

SABIC Innovative Plastics Asia Pacific

Message:

LEXAN LUX9610 is a flame retardant transparent polycarbonate featuring non brominated and non chlorinated FR system with good flow and thin wall FR performance. It intended to meet WEEE/RoHS requirements for various applications.

General Information			
UL YellowCard	E207780-100792480	E207780-101309028	
Features	Bromine Free		
	Chlorine Free		
	Flame Retardant		
	Good Flow		
Uses	Thin-walled Parts		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.60 to 0.80	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.35	%	
Equilibrium, 23°C, 50% RH	0.15	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2300	MPa	ASTM D638
--	2230	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	62.0	MPa	ASTM D638
Yield	62.0	MPa	ISO 527-2/50
Break ³	65.0	MPa	ASTM D638
Break	58.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	6.0	%	ASTM D638
Yield	6.0	%	ISO 527-2/50
Break ⁵	85	%	ASTM D638
Break	77	%	ISO 527-2/50
Flexural Modulus			
50.0 mm Span ⁶	2160	MPa	ASTM D790

-- ⁷	2250	MPa	ISO 178
Flexural Stress			
--	95.0	MPa	ISO 178
Yield, 50.0 mm Span ⁸	95.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	760	J/m	ASTM D256
23°C ⁹	70	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	70.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed, 64.0 mm Span ¹⁰	136	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	125	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹¹	125	°C	ISO 75-2/Af
Vicat Softening Temperature	142	°C	ASTM D1525 ¹²
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE			ASTM E831
Flow : -40 to 40°C	6.8E-5	cm/cm/°C	
Transverse : -40 to 40°C	6.7E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 3		UL 746
High Amp Arc Ignition (HAI)	PLC 1		UL 746
Hot-wire Ignition (HWI)	PLC 3		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Glow Wire Flammability Index (1.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
1.00 mm	850	°C	
1.50 mm	850	°C	
Optical	Nominal Value	Unit	Test Method
Transmittance (2000 µm)	89.0	%	Internal Method
Haze (2000 µm)	1.0	%	Internal Method
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 to 80.0	°C	
Rear Temperature	260 to 280	°C	
Middle Temperature	270 to 290	°C	
Front Temperature	280 to 310	°C	
Nozzle Temperature	270 to 290	°C	

Processing (Melt) Temp	280 to 310	°C
Mold Temperature	80.0 to 110	°C
NOTE		
1.	5.0 mm/min	
2.	Type I, 50 mm/min	
3.	Type I, 50 mm/min	
4.	Type I, 50 mm/min	
5.	Type I, 50 mm/min	
6.	1.3 mm/min	
7.	2.0 mm/min	
8.	1.3 mm/min	
9.	80*10*3	
10.	80*10*4 mm	
11.	80*10*4 mm	
12.	Rate B (120°C/h), Loading 2 (50 N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT