

MBA ABS 4134 70/05

Acrylonitrile Butadiene Styrene
MBA Polymers Austria Kunststoffverarbeitung GmbH

Message:
An easy flowing, post-consumer recycled acrylonitrile-butadiene-styrene copolymer for general use. Available in mouse grey (reference 70/05).

General Information			
Recycled Content	Yes		
Features	Copolymer		
	Good liquidity		
	General		
Uses	General		
Appearance	Grey		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm ³	Internal method
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	24	g/10 min	ISO 1133

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2500	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	41.0	MPa	ISO 527-2/50
Flexural Modulus ¹ (23°C)	2400	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	11	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C)	12	kJ/m ²	ISO 180/1A

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	92.0	°C	ISO 306/B50

Injection	Nominal Value	Unit
Drying Temperature	80	°C
Drying Time	3.0 - 4.0	hr
Suggested Max Moisture	0.050 - 0.10	%
Processing (Melt) Temp	210 - 250	°C
Mold Temperature	40 - 60	°C

Extrusion	Nominal Value	Unit
Drying Temperature	80	°C
Drying Time	3.0 - 4.0	hr

Suggested Max Moisture	0.050 - 0.10	%
Melt Temperature	200 - 220	°C
NOTE		
1.	2.0 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

