

Polimid A 25 GF V0A TR1

Polyamide 66

Poliblend S.p.a.

Message:

Polimid A 25 GF V0A TR1 is a Polyamide 66 (Nylon 66) material filled with 25% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America. Primary attribute of Polimid A 25 GF V0A TR1: Flame Rated.

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Additive	Halogen		
Features	Good Electrical Properties		
	Halogenated		
	Self Extinguishing		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm ³	ISO 1183
Molding Shrinkage	0.40 to 0.60	%	
Water Absorption (23°C, 24 hr)	0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9000	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	125	MPa	
Break	125	MPa	
Tensile Strain			ISO 527-2
Yield	2.5	%	
Break	2.5	%	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	6.5	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	40	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	258	°C	ISO 75-2/B
1.8 MPa, Unannealed	243	°C	ISO 75-2/A
Continuous Use Temperature ¹	125	°C	
Vicat Softening Temperature	253	°C	ISO 306/A120
Ball Pressure Test (165°C)	Pass		IEC 60695-10-2
Melting Temperature	260	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	400	V	IEC 60112

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	V-0		
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (2.00 mm)	850	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	> 3.0	hr	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	80.0 to 90.0	°C	
NOTE			
1.	Without Load		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

