

LEXAN™ 500R resin

Polycarbonate

SABIC Innovative Plastics

Message:

10% GR PC. Optimum combination of high modulus plus excellent impact strength and flame retardance. Internal mold release.

General Information			
UL YellowCard	E45587-236877	E207780-100726438	
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Additive	demoulding		
Features	Rigidity, high		
	Impact resistance, good		
	Flame retardancy		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			ASTM D792
--	1.27	g/cm³	ASTM D792
--	1.25	g/cm³	ASTM D792
Specific Volume	0.802	cm³/g	ASTM D792
Radiant Panel Listing (UL)	YES		
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	7.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.20 - 0.40	%	Internal method
Water Absorption			ASTM D570
24 hr	0.12	%	ASTM D570
Equilibrium, 23°C	0.31	%	ASTM D570
Outdoor Suitability	f2		UL 746C
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
Class m	85		ASTM D785
Class r	124		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	66.2	MPa	ASTM D638
Fracture	55.2	MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Yield	8.0	%	ASTM D638
Fracture	15	%	ASTM D638
Flexural Modulus ³ (50.0 mm Span)	3450	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 50.0 mm Span)	103	MPa	ASTM D790

Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	11.0	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Unnotched Izod Impact (23°C)	2100	J/m	ASTM D4812
Dart Drop Impact (23°C)	102	J	ASTM D3029
Tensile Impact Strength ⁵	158	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm	146	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	142	°C	ASTM D648
Vicat Softening Temperature	154	°C	ASTM D1525 ⁶
CLTE - Flow (-40 to 95°C)	3.2E-5	cm/cm/°C	ASTM E831
Specific Heat	1210	J/kg/°C	ASTM C351
Thermal Conductivity	0.20	W/m/K	ASTM C177
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+17	ohms · cm	ASTM D257
Dielectric Strength (3.20 mm, in Air)	18	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
50 Hz	3.10		ASTM D150
60 Hz	3.10		ASTM D150
1 MHz	3.05		ASTM D150
Dissipation Factor			ASTM D150
50 Hz	8.0E-4		ASTM D150
60 Hz	8.0E-4		ASTM D150
1 MHz	7.5E-3		ASTM D150
Arc Resistance ⁷	PLC 7		ASTM D495
Comparative Tracking Index (CTI)	PLC 3		UL 746
High Amp Arc Ignition (HAI)	PLC 4		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 4		UL 746
Hot-wire Ignition (HWI)	PLC 1		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.52 mm	V-0		UL 94
3.05 mm	5VA		UL 94
Oxygen Index	36	%	ASTM D2863
Injection	Nominal Value	Unit	Test Method
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	

Drying Time, Maximum	48	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	40 - 60	%
Rear Temperature	288 - 310	°C
Middle Temperature	299 - 321	°C
Front Temperature	310 - 332	°C
Nozzle Temperature	304 - 327	°C
Processing (Melt) Temp	310 - 332	°C
Mold Temperature	82.2 - 116	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	40 - 70	rpm
Vent Depth	0.025 - 0.076	mm

NOTE

- | | |
|----|---------------------------|
| 1. | Type 1, 5.0 mm/min |
| 2. | Type 1, 5.0 mm/min |
| 3. | 1.3 mm/min |
| 4. | 1.3 mm/min |
| 5. | Type S |
| 6. | 标准 B (120°C/h), 载荷2 (50N) |
| 7. | Tungsten electrode |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT