

RTP 2299 X 115088 G

Polyetheretherketone

RTP Company

Message:

Glass Fiber - Carbon Nanotube - ESD Protection

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
	Carbon nano filler		
Features	Electrostatic discharge protection		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.59	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.20 - 0.30	%	ASTM D955
Moisture Content	0.10	%	
Static Decay		sec	FTMS 101C 4046.1
Primary Additive	35	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12800	MPa	ASTM D638
Tensile Strength	186	MPa	ASTM D638
Tensile Elongation (Yield)	2.5	%	ASTM D638
Flexural Modulus	12800	MPa	ASTM D790
Flexural Strength	303	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (3.20 mm)	850	J/m	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity			
--	1.0E+5 - 1.0E+7	ohms	ASTM D257
--	1.0E+4 - 1.0E+6	ohms	ESD STM11.11
Volume Resistivity	10 - 1.0E+3	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	3.0	hr	
Dew Point	-28.9	°C	
Processing (Melt) Temp	349 - 399	°C	
Mold Temperature	163 - 218	°C	
Injection Pressure	82.7 - 124	MPa	
Injection instructions			

Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

