

Razalen® Q121

Polypropylene Homopolymer

Razin™ Engineering Plastics

Message:

Razalen Q121 is a general purpose injection grade black color homopolymer polypropylene.

General Information			
Features	General Purpose Homopolymer		
Uses	General Purpose		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.5	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	32.0	MPa	ASTM D638
Tensile Elongation (Break)	13	%	ASTM D638
Flexural Modulus	1500	MPa	ASTM D790
Flexural Strength	40.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	3.00	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	95.0	°C	ASTM D648
Vicat Softening Temperature	152	°C	ASTM D1525
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	1.0 to 2.0	hr	
Rear Temperature	200 to 220	°C	
Middle Temperature	200 to 220	°C	
Front Temperature	200 to 220	°C	
Processing (Melt) Temp	200 to 230	°C	
Mold Temperature	30.0 to 60.0	°C	
Injection Pressure	50.0 to 150	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT