

Sylvin 9925-60 Natural

Flexible Polyvinyl Chloride
Sylvin Technologies Incorporated

Message:

Sylvin Compounds 9925-60 Natural is a Flexible Polyvinyl Chloride material filled with filler. It is available in North America for injection molding. Typical applications include:
Caps/Lids/Closures
Coating Applications
Handles
Hose/Tubing
Seating

General Information			
Filler / Reinforcement	Filler		
Uses	Caps		
	Flexible Grips		
	Hose Fittings		
	Protective Coverings		
	Seats		
Appearance	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.7 to 2.2	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	9.65	MPa	ASTM D638
Tensile Elongation (Break)	480	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	33.3	kN/m	ASTM D624
Injection	Nominal Value	Unit	
Processing (Melt) Temp	154 to 166	°C	
Mold Temperature	21.1 to 37.8	°C	
Injection Rate	Moderate-Fast		
Back Pressure	0.414 to 0.689	MPa	
Screw Speed	35 to 50	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

