

# Premi-Glas® 1201-15

Thermoset, Unspecified

Premix, Inc.

## Message:

Premi-Glas® 1201-15 is a fiberglass reinforced thermoset sheet molding compound for sanitary ware applications such as shower bases and surrounds, bathtubs, and vanity tops.

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Good Dimensional Stability		
	High Gloss		
Appearance	Bone		
	White		
Forms	SMC - Sheet Molding Compound		
Processing Method	Compression Molding		
Physical	Nominal Value	Unit	
Specific Gravity	1.76	g/cm <sup>3</sup>	
Molding Shrinkage - Flow	0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9000	MPa	ASTM D638
Tensile Strength	35.0	MPa	ASTM D638
Flexural Modulus	9000	MPa	ASTM D790
Flexural Strength	90.0	MPa	ASTM D790
Poisson's Ratio	0.30		
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	370	J/m	ASTM D256
Unnotched Izod Impact	430	J/m	ASTM D256
Thermal	Nominal Value	Unit	
CLTE			
Flow <sup>1</sup>	2.5E-5	cm/cm/°C	
Transverse <sup>2</sup>	3.5E-5	cm/cm/°C	
Thermal Conductivity	0.30	W/m/K	
Flammability	Nominal Value	Test Method	
Flame Resistance (3.00 mm)	Pass	ANSI Z124.2	
Stain Resistance	Pass	ANSI Z124.2	
Injection	Nominal Value	Unit	
Mold Temperature	150	°C	
Injection Pressure	3.50 to 6.50	MPa	

## NOTE

- |    |              |
|----|--------------|
| 1. | XY Direction |
| 2. | Z Direction  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT