

Trexprene® A80BW

Thermoplastic Vulcanizate

Mitsubishi Chemical Performance Polymers, Inc.

Message:

Product Description: TREXPRENE ® A80BW is a heat and UV stabilized PP/EPDM based Thermoplastic Vulcanized Elastomer (TPV) and is primarily intended for Exterior applications. This material can be processed using Extrusion, Injection, or Blow Molding equipment.

General Information	
Additive	Heat Stabilizer
	UV Stabilizer
Features	Good UV Resistance
	Heat Stabilized
Uses	Automotive Exterior Parts
Forms	Pellets
Processing Method	Blow Molding
	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	0.930 to 0.970	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 15 sec)	76 to 84		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress - Across Flow ¹ (100% Strain)	4.00	MPa	ISO 37
Tensile Stress - Across Flow ² (Yield)	9.20	MPa	ISO 37
Tensile Elongation - Across Flow ³ (Break)	660	%	ISO 37
Tear Strength - Across Flow ⁴	47	kN/m	ISO 34-1
Compression Set			
70°C, 22 hr	42	%	ASTM D395B
125°C, 70 hr	56	%	ASTM D395B
70°C, 22 hr ⁵	42	%	ISO 815
125°C, 70 hr ⁶	56	%	ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (135°C, 1000 hr)	-0.80	%	ISO 188
Change in Tensile Strain at Break in Air (135°C, 1000 hr)	-8.6	%	ISO 188
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature			

--	-54.0	°C	ASTM D746
Type B	-54.0	°C	ISO 812
Additional Information	Nominal Value		Test Method
Accelerated Weathering Duration ⁷	Delta E < 3		SAE J2527
Ozone Resistance (40°C) ⁸	0 Rating		ISO 1431-1
Weatherability ⁹			SAE J1976
Arizona	Delta E < 3		
Florida	Delta E < 3		
NOTE			
1.	Type 1, 500 mm/min		
2.	Type 1, 500 mm/min		
3.	Type 1, 500 mm/min		
4.	Method Ba, Angle (Unnicked), 500 mm/min		
5.	Type A		
6.	Type A		
7.	Extended UV Filters, 2500 kJ/m 2		
8.	100 pphm, Method A		
9.	2 years exposure, Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

