

SUMIPEX® BF3

Polymethyl Methacrylate Acrylic
Sumitomo Chemical Co., Ltd.

Message:

SUMIPEX® BF3 is a Polymethyl Methacrylate Acrylic material. It is available in Asia Pacific, Europe, or North America. Primary attribute of SUMIPEX® BF3: Flame Rated.

General Information			
UL File Number	E54705B		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.19	g/cm ³	JIS K7112
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	3.0	g/10 min	JIS K7210
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	370		JIS K7202
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	72.0	MPa	JIS K7113
Tensile Elongation (Break)	7.0	%	JIS K7113
Flexural Modulus	3100	MPa	JIS K7203
Flexural Strength	110	MPa	JIS K7203
Flexural Rigidity	4.0	%	JIS K7203
Die Swell Comparison	1.80		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.7	kJ/m ²	JIS K7110
Charpy Unnotched Impact Strength	1.4	kJ/m ²	JIS K7110
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ² (1.8 MPa, Annealed)	91.0	°C	JIS K7207
Vicat Softening Temperature	96.0	°C	JIS K7206
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm, All Colors)	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		JIS K7105
Transmittance ³	93.0	%	JIS K7105
Haze	< 0.50	%	JIS K7105
NOTE			
1.	Method A		
2.	VST 25±3, 4 hrs		
3.	Method A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

