

Maxxam™ FR X MF-6780-001-2 Black

Polypropylene

PolyOne Corporation

Message:

Maxxam™ FR flame-retardant polyolefin compounds and masterbatches meet stringent flammability performance requirements defined by industry agencies, including Underwriters Laboratories UL 94 V-2, V-0, and 5VA performance ratings. In addition, many compounds in the Maxxam FR portfolio offer elevated Relative Thermal Index (RTI) ratings. X MF-6780-001-2 Black is designed to impart good flame retardancy to polypropylene homopolymer as well as co-polymer. The letdown ratios will vary from one grade of polypropylene to another. When this concentrate is letdown at the proper ratio the resulting materials can achieve flame retardancy equivalent to the requirements of the UL-94 V-2 or VTM-2. Typical starting points for formulation range from 10-15% by weight of X MF-6780-001-2 Black.

General Information			
Features	Flame retardancy		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (230°C/2.16 kg)	50	g/10 min	ASTM D1238
NOTE			
1.	Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

