# Hostacom X M1 T02 357026

#### Polypropylene

LyondellBasell Industries

#### Message:

Hostacom X M1 T02 is a 15% talc filled elastomer modified PP, with excellent impact/stiffness balance and very good processability. This product is also available in other colors, new colors can be developed depending on customer requirements.

For regulatory compliance information, see Hostacom X M1 T02 357026 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Talc filler, 15% filler by weight		
Features	Rigid, good		
	Impact resistance, high		
	Impact resistance, good		
	Good UV resistance		
	Workability, good		
	Good color stability		
	Good wear resistance		
	Medium liquidity		
	The smell is low to none		
	ductility		
	Excellent appearance		
Uses	Application in Automobile Field		
	Car interior parts		
	Car dashboard		
Appearance	Available colors		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.01	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	11	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus <sup>1</sup> (23°C)	1700	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	17	kJ/m²	ISO 179/1eA
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

