

AVP™ KLL10CP

Polycarbonate
SABIC Innovative Plastics

Message:

AVP™ KLL10CP is a Polycarbonate (PC) product filled with 10% glass fiber. It can be processed by injection molding and is available in North America. Applications of AVP™ KLL10CP include electrical/electronic applications, appliances and automotive. Characteristics include:

- Flame Rated
- Eco-Friendly/Green
- Flame Retardant
- Good Toughness
- High Strength

General Information			
UL YellowCard	E121562-296851		
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Recycled Content	Yes		
Features	Flame Retardant		
	Good Toughness		
	High Rigidity		
	High Strength		
Uses	Appliance Components		
	Automotive Applications		
	Communication Applications		
	Electrical Parts		
UL File Number	E134027		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3100	MPa	ASTM D638
Tensile Strength ¹ (Yield, 3.18 mm)	62.1	MPa	ASTM D638
Tensile Elongation ² (Break, 3.18 mm)	15	%	ASTM D638
Flexural Modulus ³ (3.18 mm, 50.8 mm Span)	3170	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 3.18 mm, 50.8 mm Span)	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact (23°C, 3.18 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.35 mm)	138	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (2.29 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	6.0	hr	
Drying Time, Maximum	16	hr	
Rear Temperature	282 to 293	°C	
Middle Temperature	288 to 316	°C	
Front Temperature	288 to 316	°C	
Nozzle Temperature	288 to 316	°C	
Processing (Melt) Temp	304 to 332	°C	
Mold Temperature	82.2 to 116	°C	
Back Pressure	0.345 to 1.38	MPa	
NOTE			
1.	51 mm/min		
2.	51 mm/min		
3.	1.3 mm/min		
4.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

