Tarflen® SM-B30

Polytetrafluoroethylene

Grupa Azoty S.A.

Message:

Tarflen® SM-B30 is a polytetrafluoroethylene (PTFE) material, which contains 30% bronze filler. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

Tarflen® The main features of the SM-B30 are:

Flame Retardant

good weather resistance

chemical resistance

Wear-resistant

Typical application areas include:

engineering/industrial accessories

application of coating

Wire and cable

Mechanical

Sealing applications

Hose

| General Information | | | | | |
|-------------------------|-------------------------------------|-------|-------------|--|--|
| Filler / Reinforcement | Bronze filler, 30% filler by weight | | | | |
| Features | Low friction coefficient | | | | |
| | Moisture proof | | | | |
| | Good chemical resistance | | | | |
| | Good wear resistance | | | | |
| | Good weather resistance | | | | |
| | Flame retardancy | | | | |
| | | | | | |
| Uses | Cable sheath | | | | |
| | Washer | | | | |
| | Valve/valve components | | | | |
| | Pipe | | | | |
| | Piping system | | | | |
| | Seals | | | | |
| | Accessories | | | | |
| | Coating application | | | | |
| | Fabric coating | | | | |
| | | | | | |
| Forms | Particle | | | | |
| Physical | Nominal Value | Unit | Test Method | | |
| Density | 2.80 | g/cm³ | ISO 1183 | | |
| Molding Shrinkage | | | ISO 294-4 | | |
| Vertical flow direction | 2.0 - 3.5 | % | ISO 294-4 | | |
| Flow direction | 3.0 | % | ISO 294-4 | | |
| | | | | | |

Unit

Test Method

Nominal Value

| Tensile Stress (Yield) | 18.0 | MPa | ISO 527-2 |
|--------------------------------------|---------------|----------|-------------|
| Tensile Strain (Break) | 280 | % | ISO 527-2 |
| Thermal | Nominal Value | Unit | Test Method |
| Linear thermal expansion coefficient | | | ISO 11359-2 |
| Flow: 23 to 100°C | 1.2E-4 | cm/cm/°C | ISO 11359-2 |
| Lateral: 23 to 100°C | 8.5E-5 | cm/cm/°C | ISO 11359-2 |
| Extrusion instructions | | | |

Molding Pressure: 40 to 60 MpaMolding Temperature: 360 °C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

