

Ad-Tech Epoxy EL-301-LP

Epoxy; Epoxide

Ad-Tech Plastic Systems Corp.

Message:

Ad-Tech Epoxy EL-301-LP is an Epoxy; Epoxide (Epoxy) product. It can be processed by laminating and is available in North America. Applications of Ad-Tech Epoxy EL-301-LP include adhesives/tapes, coating applications and tools.

Characteristics include:

Good Adhesion

Good Aesthetics

Good Dimensional Stability

General Information			
Features	Good Adhesion		
	Good Dimensional Stability		
	Good Surface Finish		
Uses	Adhesives		
	Laminates		
	Molds/Dies/Tools		
Appearance	Amber		
Forms	Liquid		
Processing Method	Laminating		
Physical	Nominal Value	Unit	Test Method
Apparent Density	1.10	g/cm ³	ASTM D1895
Molding Shrinkage - Flow	0.42	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	86		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	22100	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	154	MPa	
Ultimate	309	MPa	
Tensile Elongation (Yield)	1.8	%	ASTM D638
Flexural Modulus	13800	MPa	ASTM D790
Flexural Strength (Yield)	228	MPa	ASTM D790
Compressive Strength	92.3	MPa	ASTM D695
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	80.0	°C	ASTM D648
CLTE - Flow	4.8E-5	cm/cm/°C	ASTM D696
Thermoset	Nominal Value	Unit	Test Method


Thermoset Components			
Hardener	Mix Ratio by Volume: 1.0		
Resin	Mix Ratio by Weight: 33		
	Mix Ratio by Weight: 100		
Pot Life (25°C)	Mix Ratio by Volume: 2.6		
	50 to 60	min	
	Thermoset Mix Viscosity	3500	cP
Demold Time (25°C)	4300 to 7200	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT