

LEXAN™ FXEMPX2L resin

Polycarbonate

SABIC Innovative Plastics Asia Pacific

Message:

Opaque EXL, UV-Stabilized & light shielding capability, for portable electronics device enclosure application. Only available in white, grey and limited pastel colors. Consult CIC or PM for color availability & limitation.

General Information			
Additive	UV stabilizer		
Features	Good UV resistance		
Uses	Electrical housing		
Appearance	White		
	Opacity		
	Grey		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	12.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2040	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	52.0	MPa	ASTM D638
Fracture	46.0	MPa	ASTM D638
Tensile Elongation ³			ASTM D638
Yield	5.0	%	ASTM D638
Fracture	68	%	ASTM D638
Flexural Modulus ⁴ (50.0 mm Span)	1970	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 50.0 mm Span)	80.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	530	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	114	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60 - 80	°C	
Rear Temperature	260 - 280	°C	

Middle Temperature	280 - 305	°C
Front Temperature	295 - 315	°C
Nozzle Temperature	290 - 310	°C
Processing (Melt) Temp	295 - 315	°C
Mold Temperature	70 - 95	°C

NOTE

1.	50 mm/min
2.	Type 1, 50mm/min
3.	Type 1, 50mm/min
4.	1.3 mm/min
5.	1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

