

Durethan® BKV 230 H2.0 DUS008 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 30 % glass fibers, injection molding, improved impact strength, heat-aging stabilized

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Additive		Heat Stabilizer		
Features		Good Impact Resistance		
		Heat Stabilized		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.32	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Across Flow : 280°C, 2.00 mm ¹	0.85	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.14	--	%	
Flow : 280°C, 2.00 mm ³	0.35	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.040	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	8600	4400	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	130	85.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.5	8.0	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	7500	4400	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% Strain,23°C	205	105	MPa	
23°C ⁶	210	125	MPa	
Flexural Strain at Flexural Strength ⁷ (23°C)	4.5	6.2	%	ISO 178/A
ISO Shortname	PA 6-HI, GHR, 14-090, GF30	--		ISO 1874
Residual Moisture Content	0.030 to 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact Strength				ISO 180/1A
-30°C	14	15	kJ/m ²	
23°C	23	35	kJ/m ²	
Unnotched Izod Impact Strength				ISO 180/1U

-30°C	75	75	kJ/m ²	
23°C	75	90	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	218	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	198	--	°C	ISO 75-2/A
Melting Temperature ⁸	220	--	°C	ISO 11357-3
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	260 to 290		°C	
Mold Temperature	80.0 to 100		°C	
NOTE				

- | | |
|----|-----------------------------|
| 1. | 60x60x2mm, 80°C MT, 600 bar |
| 2. | 60x60x2mm |
| 3. | 60x60x2mm, 80°C MT, 600 bar |
| 4. | 60x60x2mm |
| 5. | 2.0 mm/min |
| 6. | 2.0 mm/min |
| 7. | 2 mm/min |
| 8. | 10°C/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT