

# Kumho EP HAC 8265

Polycarbonate + ABS

Korea Kumho Petrochemical Co., Ltd.

Message:

Features: High Impact and High Heat Resistant  
Applications: Automotive glove box, Instrumental Panel

| General Information                                     |                                   |                   |                         |
|---------------------------------------------------------|-----------------------------------|-------------------|-------------------------|
| Features                                                | High Heat Resistance              |                   |                         |
|                                                         | High Impact Resistance            |                   |                         |
| Uses                                                    | Automotive Applications           |                   |                         |
|                                                         | Automotive Instrument Panel       |                   |                         |
|                                                         | Automotive Interior Parts         |                   |                         |
| RoHS Compliance                                         | RoHS Compliant                    |                   |                         |
| UL File Number                                          | E65424                            |                   |                         |
| Physical                                                | Nominal Value                     | Unit              | Test Method             |
| Specific Gravity                                        | 1.14                              | g/cm <sup>3</sup> | ASTM D792               |
| Melt Mass-Flow Rate (MFR) (230°C/21.6 kg)               | 38                                | g/10 min          | ASTM D1238              |
| Molding Shrinkage - Flow                                | 0.50 to 0.70                      | %                 | ASTM D955               |
| Hardness                                                | Nominal Value                     | Unit              | Test Method             |
| Rockwell Hardness (R-Scale)                             | 115                               |                   | ASTM D785               |
| Mechanical                                              | Nominal Value                     | Unit              | Test Method             |
| Tensile Strength (Yield)                                | 53.9                              | MPa               | ASTM D638               |
| Tensile Elongation (Yield)                              | 110                               | %                 | ASTM D638               |
| Flexural Modulus                                        | 2160                              | MPa               | ASTM D790               |
| Flexural Strength (Yield)                               | 76.5                              | MPa               | ASTM D790               |
| Impact                                                  | Nominal Value                     | Unit              | Test Method             |
| Notched Izod Impact (23°C, 6.40 mm)                     | 540                               | J/m               | ASTM D256               |
| Thermal                                                 | Nominal Value                     | Unit              | Test Method             |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 110                               | °C                | ASTM D648               |
| Vicat Softening Temperature                             | 125                               | °C                | ASTM D1525 <sup>1</sup> |
| Flammability                                            | Nominal Value                     |                   | Test Method             |
| Flame Rating (1.60 mm)                                  | HB                                |                   | UL 94                   |
| NOTE                                                    |                                   |                   |                         |
| 1.                                                      | Rate A (50°C/h), Loading 2 (50 N) |                   |                         |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

