

# TAISOX 2210

Linear Low Density Polyethylene  
Formosa Plastics Corporation

## Message:

TAISOX 2210 is a linear low density polyethylene material. This product is available in North America, Europe or Asia Pacific region. The processing method is blow molded film.

The main features of TAISOX 2210 are:

- Antiblock software
- Good tear strength
- Good sealing performance
- Impact resistance
- Puncture resistance

Typical application areas include:

- bag/lining
- Wrapping
- Movie

General Information			
Additive	Moderate caking resistance		
Features	Low density		
	Perforation resistance		
	Impact resistance, high		
	Good heat sealability		
	Good tear strength		
	Moderate caking resistance		
Uses	Films		
	Stretch winding		
	Heavy packing bag		
Forms	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	38	µm	ASTM D882
secant modulus			
1% secant, MD: 38 µm, blown film	186	MPa	
1% secant, TD: 38 µm, blown film	235	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 38 µm, blown film	10.3	MPa	ASTM D882
TD: Yield, 38 µm, blown film	10.8	MPa	ASTM D882

MD: Broken, 38 µm, blown film	41.2	MPa	ASTM D882
TD: Broken, 38 µm, blown film	33.3	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 38 µm, blown film	580	%	ASTM D882
TD: Broken, 38 µm, blown film	760	%	ASTM D882
Dart Drop Impact (38 µm, Blown Film)	260	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD: 38 µm, blown film	360	g	ASTM D1922
TD: 38 µm, blown film	820	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-70.0	°C	ASTM D746
Vicat Softening Temperature	93.0	°C	ASTM D1525
Melting Temperature	122	°C	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 38.0 µm, Blown Film)	51		ASTM D2457
Clarity	65.0		ASTM D1746
Haze (38.0 µm, Blown Film)	13	%	ASTM D1003
Additional Information			

Blow Up Ratio: 2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT