

Cellidor B 631-10S

Cellulose Acetate Butyrate

ALBIS PLASTIC GmbH

Message:

Cellidor B 631-10S is a Cellulose Acetate Butyrate (CAB) product. It can be processed by extrusion or profile extrusion and is available in Asia Pacific, Europe, or North America. Typical application: Sporting Goods.

Characteristics include:

REACH Compliant

RoHS Compliant

Plasticized

Eco-Friendly/Green

General Information			
Additive	Plasticizer		
Features	Non-Phthalate Plasticizer		
	Renewable Resource Content		
Uses	Profiles		
	Sporting Goods		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Processing Method	Extrusion		
	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (210°C/2.16 kg)	6.00	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 132/30)	65.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1600	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	37.0	MPa	
Break	33.0	MPa	
Tensile Strain (Yield)	18	%	ISO 527-2
Flexural Stress (3.5% Strain)	47.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
--	18	kJ/m ²	
-30°C	7.0	kJ/m ²	

Charpy Unnotched Impact Strength	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	90.0	°C	ISO 75-2/A
Vicat Softening Temperature	90.0	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+17	ohms·cm	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature			
Circulation Dryer	50.0 to 70.0	°C	
Desiccant Dryer	50.0 to 70.0	°C	
Drying Time			
Circulation Dryer	2.0 to 4.0	hr	
Desiccant Dryer	1.0 to 2.0	hr	
Extrusion	Nominal Value	Unit	
Melt Temperature	190 to 235	°C	
Die Temperature	40.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT