

# Syncure™ V0044G-UV RoHS Natural

Crosslinked Polyethylene

PolyOne Corporation

Message:

Available as Flame Retardant Catalyst Masterbatch component for PolyOne Syncure System S110FV-UV.

General Information			
Features	Flame Retardant		
	Sunlight Resistant (720 hours)		
Uses	Wire & Cable Applications		
Agency Ratings	UL 4703		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.24	g/cm <sup>3</sup>	ASTM D792
Apparent Density <sup>1</sup>	1.25	g/cm <sup>3</sup>	Internal Method
Melt Mass-Flow Rate (MFR) <sup>2</sup> (190°C/2.16 kg)	3.4	g/10 min	ASTM D1238
NOTE			
1.	Geon® 1169		
2.	Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT