

MAJORIS FE124HP - 9700

Polypropylene

AD majoris

Message:

FE124HP - 9700 is part of a new material family with low halogen no blooming flame retardant, high impact strength, high gloss and antistatic as well as an excellent UV-resistance and very low war page behaviour. Intended for injection moulding. The product is available in natural (FE124HP) but other colours can be provided on request.

APPLICATIONS

FE124HP - 9700 is recommended for indoor or outdoor electrical and lighting applications like plugs, sockets, connectors, capacitor housings, small junction boxes or lamp covers; where chemical resistance, impact and flammability behaviours are required.

General Information			
Additive	Antistatic		
	Flame Retardant		
Features	Antistatic		
	Flame Retardant		
	Good Chemical Resistance		
	Good UV Resistance		
	High Gloss		
	High Impact Resistance		
	Low Halogen Content		
	Low Warpage		
	Non-Blooming		
	Recyclable Material		
Uses	Connectors		
	Electrical Housing		
	Electrical/Electronic Applications		
	Lighting Applications		
	Outdoor Applications		
	Plugs		
Appearance	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.995	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133

Spiral Flow ¹	99.0	cm	
Molding Shrinkage			
Across Flow	1.3	%	
Flow : 2.00 mm	1.2	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1700	MPa	ISO 527-2
Tensile Stress			
Yield	26.0	MPa	ISO 527-2/50
Break	17.0	MPa	ISO 527-2
Tensile Strain			
Yield	5.0	%	ISO 527-2/50
Break	57	%	ISO 527-2
Flexural Modulus	1500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	2.0	kJ/m ²	
23°C	4.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-20°C	38	kJ/m ²	
23°C	100	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	92.0	°C	ISO 75-2/B
Vicat Softening Temperature			
--	153	°C	ISO 306/A
--	80.0	°C	ISO 306/B
Ball Pressure Test (125°C)	Pass		IEC 60335-1
RTI Elec	110	°C	UL 746
RTI Imp	115	°C	UL 746
RTI Str	115	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	3.0E+15	ohms	IEC 60093
Volume Resistivity	1.4E+16	ohms · cm	IEC 60093
Electric Strength	42	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
50 Hz	2.35		
1 kHz	2.31		
100 kHz	2.32		
Dissipation Factor			IEC 60250
50 Hz	1.1E-3		
1 kHz	1.0E-3		
100 kHz	2.6E-3		

Arc Resistance (3.00 mm)	PLC 5		ASTM D495
Comparative Tracking Index (CTI) (3.00 mm)	PLC 0		UL 746
Comparative Tracking Index			IEC 60112
--	> 600	V	
Solution B	> 600	V	
Needle Flame Test (1.00 mm)	Pass		IEC 60695-11-5
High Amp Arc Ignition (HAI)			UL 746
1.50 mm	PLC 0		
3.00 mm	PLC 0		
High Voltage Arc Tracking Rate (HVTR)			UL 746
1.50 mm	PLC 0		
3.00 mm	PLC 0		
Hot-wire Ignition (HWI)			UL 746
1.50 mm	PLC 3		
3.00 mm	PLC 2		
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm, All)	V-2		UL 94
Glow Wire Flammability Index			IEC 60695-2-12
0.500 mm	850	°C	
3.00 mm	960	°C	
Glow Wire Ignition Temperature (1.00 mm)	850	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Processing (Melt) Temp	180 to 200	°C	
Mold Temperature	20.0 to 50.0	°C	
NOTE			

1. Melt Temperature: 200°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

