

TORZEN® GT3300HS1L NC01

Polyamide 66
INVISTA Engineering Polymers

Message:

TORZEN® GT3300HS1L NC01 is a 33% glass reinforced, impact modified, heat stabilized, natural, PA66 resin suitable for many injection molding applications where high tensile strength and dimensional stability are needed.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 33% filler by weight		
Additive	Impact modifier heat stabilizer		
Features	Good dimensional stability Impact modification High tensile strength Thermal Stability Good demoulding performance		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.34	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Vertical flow direction: 2.00mm	0.50 - 0.70	%	ISO 294-4
Flow direction: 2.00mm	0.30 - 0.50	%	ISO 294-4
Water Absorption			ISO 62
23°C, 24 hr	1.1	%	ISO 62
Equilibrium, 23°C, 50% RH	1.7	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10000	MPa	ISO 527-2
Tensile Stress (Break)	170	MPa	ISO 527-2
Tensile Strain (Break)	4.0	%	ISO 527-2
Flexural Modulus	7900	MPa	ISO 178
Flexural Stress	250	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-40°C	15	kJ/m ²	ISO 179
23°C	22	kJ/m ²	ISO 179

Notched Izod Impact (23°C)	20	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	260	°C	ISO 75-2/B
1.8 MPa, not annealed	247	°C	ISO 75-2/A
Melting Temperature ¹	262	°C	ISO 11357-3
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.080 - 0.18	%	
Rear Temperature	250 - 270	°C	
Middle Temperature	270 - 290	°C	
Front Temperature	270 - 290	°C	
Nozzle Temperature	270 - 290	°C	
Processing (Melt) Temp	280 - 300	°C	
Mold Temperature	50.0 - 90.0	°C	
Back Pressure	0.200 - 1.00	MPa	
Cushion	4.00 - 6.00	mm	
Vent Depth	7.0E-3 - 0.040	mm	
Injection instructions			
Screw Speed: low rpm			
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

