

Forprene® 6E1001A75

Thermoplastic Vulcanizate

SO.F.TER. SPA

Message:

Forprene® 6E1001A75 is a thermoplastic vulcanized rubber (TPV) material. This product is available in North America, Latin America or Europe. The processing method is extrusion or injection molding.

Forprene® The main features of 6E1001A75 are:

flame retardant/rated flame

Comply with REACH standard

Typical application areas include:

industrial applications

building applications

Automotive Industry

General Information			
Uses	Industrial application		
	Architectural application field		
	Application in Automobile Field		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Natural color		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	77		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (100% Strain)	2.50	MPa	ASTM D412
Tensile Strength ²	5.50	MPa	ASTM D412
Tensile Elongation ³ (Break)	500	%	ASTM D412
Tear Strength ⁴	25.0	kN/m	ASTM D624
Compression Set ⁵ (70°C, 22 hr)	48	%	ASTM D395B
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		UL 94
3.20 mm	V-0		UL 94
Oxygen Index	24	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Rear Temperature	160	°C	

Middle Temperature	170	°C
Front Temperature	180	°C
Nozzle Temperature	185	°C
Mold Temperature	20.0 - 40.0	°C
Extrusion	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	170	°C
Cylinder Zone 2 Temp.	180	°C
Cylinder Zone 3 Temp.	185	°C
Die Temperature	185	°C

Extrusion instructions

Extrusion Head Temperature: 195°C

NOTE

- | | |
|----|-------------|
| 1. | Mouth die c |
| 2. | Mouth die c |
| 3. | Mouth die c |
| 4. | C mould |
| 5. | Type 1 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT