

Akulon® F234-C

Polyamide 6
DSM Engineering Plastics

Message:

Akulon® F234-C is a polyamide 6 (nylon 6) material. This product is available in Europe, and the processing method is: film extrusion.
Akulon® The main features of the F234-C are:
high viscosity
Lubrication

General Information			
Additive	Lubricant		
Features	Lubrication		
	Viscosity, High		
Forms	Particle		
Processing Method	Film extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Viscosity Number	229	cm ³ /g	ISO 307
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ISO 8295
With itself-dynamic, cast film	1.0		ISO 8295
With itself-static, cast film	1.2		ISO 8295
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	
Tensile Modulus ¹ (50 µm, Cast Film)	450	MPa	Internal method
Tensile Stress - MD			ISO 527-3
Yield, 50 µm, cast film	32.0	MPa	ISO 527-3
50 µm, cast film	83.0	MPa	ISO 527-3
Tensile Elongation - MD (Broken, 50 µm, cast film)	350	%	ISO 527-3
Trouser Tear Resistance - MD (50 µm, Cast Film)	32.0	N/mm	ISO 6383-1
Water Vapor Transmission Rate (23°C, 85% RH, 50 µm, cast film)	35	g/m ² /24 hr	DIS 15106-1/-3
Oxygen Transmission Rate ²			DIS 15105-1/-2
0% RH : 23°C, 50.0 µm	26	cm ³ /m ² /bar/24 hr	DIS 15105-1/-2
85% RH : 23°C, 50.0 µm	38	cm ³ /m ² /bar/24 hr	DIS 15105-1/-2
Specific Heat Capacity			
--	1550	J/kg/°C	
Average: 20 to 150°C	2250	J/kg/°C	
Puncture Resistance (50.0 µm) ³	13.5	J/cm	Internal method

RSV - Formic Acid, 1g/100 ml	3.40		Internal method
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	9.0E-5	cm/cm/°C	ISO 11359-2
Optical	Nominal Value	Unit	Test Method
Transmittance (50.0 µm, Cast Film)	83.0	%	Internal method
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (260°C)	1600	Pa·s	Internal method
Additional Information	Nominal Value	Unit	Test Method
Processing parameters for cast film test specimen: Extruder Temperature: 270°C Die Temperature: 270°C Chill Roll Temperature: 110°C			
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0 - 8.0	hr	
Rear Temperature	230 - 235	°C	
Middle Temperature	235 - 250	°C	
Front Temperature	240 - 260	°C	
Nozzle Temperature	240 - 270	°C	
Processing (Melt) Temp	240 - 275	°C	
Mold Temperature	50.0 - 80.0	°C	
Injection Rate	Moderate-Fast		
Back Pressure	3.00 - 10.0	MPa	
Screw Compression Ratio	2.5:1.0		
NOTE			
1.	50 mm/min		
2.	Cast Film		
3.	Cast Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT