

KOPLA PC KBG1020F

Polybutylene Terephthalate

KOPLA Co., Ltd.

Message:

KOPLA PC KBG1020F is a Polybutylene Terephthalate (PBT) material filled with glass fiber. It is available in Asia Pacific.

Important attributes of KOPLA PC KBG1020F are:

Flame Rated

Flame Retardant

Typical application of KOPLA PC KBG1020F: Electrical/Electronic Applications

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Flame Retardant		
Uses	Electrical/Electronic Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.59	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30 to 1.2	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	113	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	4.0	%	ASTM D638
Flexural Modulus (23°C)	7060	MPa	ASTM D790
Flexural Strength (23°C)	162	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	220	°C	
1.8 MPa, Unannealed	210	°C	
Melting Temperature	222	°C	
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	26	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.70		ASTM D150
Arc Resistance	120	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

