

SUSTAPEEK FG

Polyetheretherketone

Röchling Sustaplast SE & Co. KG

Message:

- Product characteristics
- Excellent dimensional stability
- High flame retardance and self-extinguishing
- Meets the requirements of the regulation (EC) No. 1935/2004 on materials intended to come in contact with food
- Typical fields of application
- Food industry

General Information			
Features	Flame Retardant		
	Good Dimensional Stability		
	Self Extinguishing		
Uses	Non-specific Food Applications		
Agency Ratings	EC 1935/2004		
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	88		ISO 868
Ball Indentation Hardness	230	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4000	MPa	ISO 527-2
Tensile Stress (Yield)	110	MPa	ISO 527-2
Tensile Strain (Break)	20	%	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	152	°C	ISO 75-2/A
Continuous Use Temperature			
-- 1	-60.0 to 250	°C	
-- 2	< 310	°C	
CLTE - Flow	5.0E-5	cm/cm/°C	DIN 53752
Specific Heat	1340	J/kg/°C	DIN 52612
Thermal Conductivity	0.25	W/m/K	DIN 52612
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+18	ohms	IEC 60093
Volume Resistivity	4.9E+16	ohms · cm	IEC 60093
Electric Strength	20	kV/mm	IEC 60243-1

Dielectric Constant	3.20		IEC 60250
Dissipation Factor (50 Hz)	1.0E-3		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.00 mm	V-0		
6.00 mm	V-0		
NOTE			
1.	Long Term		
2.	Short Term		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

