

POCAN® B 1100 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, non-reinforced, extrusion, injection molding, improved flowability

General Information			
Features	Good Flow		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.30	g/cm ³	ISO 1183
Apparent Density	0.80	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	80.0	cm ³ /10min	ISO 1133
Water Absorption			ISO 62
Saturation, 23°C	0.50	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2700	MPa	ISO 527-2/1
Flexural Modulus ¹ (23°C)	2750	MPa	ISO 178/A
Flexural Stress			ISO 178/A
3.5% Strain, 23°C	75.0	MPa	
23°C ²	85.0	MPa	
Flexural Strain at Flexural Strength ³ (23°C)	6.0	%	ISO 178/A
ISO Shortname	PBT, G, 07-030		ISO 7792
Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	90	kJ/m ²	
23°C	130	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-40°C	< 10	kJ/m ²	
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U

-30°C	75	kJ/m ²	
23°C	90	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	160	°C	ISO 75-2/B
1.8 MPa, Unannealed	60.0	°C	ISO 75-2/A
Vicat Softening Temperature	170	°C	ISO 306/B50
Ball Pressure Test (190°C)	Pass		IEC 60695-10-2
Melting Temperature ⁴	225	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	1.3E-4	cm/cm/°C	
Transverse : 23 to 55°C	1.3E-4	cm/cm/°C	
Thermal Conductivity (23°C)	0.25	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity (23°C)	> 1.0E+15	ohms·cm	IEC 60093
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.40		
23°C, 1 MHz	3.20		
Dissipation Factor			IEC 60250
23°C, 100 Hz	2.0E-3		
23°C, 1 MHz	0.019		
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
Glow Wire Flammability Index	750	°C	IEC 60695-2-12
Oxygen Index ⁵	24	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 to 8.0	hr	
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		
3.	2 mm/min		
4.	10°C/min		
5.	Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

