

VAMPSTAT Y 25G 04 V0 30

Polyamide 66

Vamp Tech

Message:

PA 66 25% glass fiber reinforced, UL 94 V0 at 1,6 mm, with red phosphorus, surface resistivity 10^4 ohm.

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Features	Low (to None) Phosphorus Content		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.60	%	
Across Flow	0.90	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	13500	MPa	ASTM D638
Tensile Strength (Yield)	140	MPa	ASTM D638
Tensile Elongation (Break)	2.2	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	6.5	kJ/m²	ISO 180/A
Unnotched Izod Impact Strength	40	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	230	°C	ASTM D648A
RTI Elec	140	°C	UL 746
RTI Imp	140	°C	UL 746
RTI Str	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+4	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.20 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	275	°C	
Mold Temperature	90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT