

Stanyl® TS250F4D

Polyamide 46
DSM Engineering Plastics

Message:

Stanyl® TS250F4D is a Polyamide 46 (Nylon 46) material filled with 20% glass fiber. It is available in Asia Pacific.
Important attributes of Stanyl® TS250F4D are:
Flame Rated
Flame Retardant
Heat Stabilizer

General Information				
UL YellowCard		E172082-225850	E47960-101987848	
Filler / Reinforcement		Glass Fiber,20% Filler by Weight		
Additive		Flame Retardant		
		Heat Stabilizer		
Features		Flame Retardant		
		Heat Stabilized		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.56	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.80	--	%	
Flow	1.3	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	1.7	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	9200	6000	MPa	ISO 527-2
Tensile Stress (Break)	150	100	MPa	ISO 527-2
Tensile Strain (Break)	2.0	4.0	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	8.0	8.0	kJ/m ²	
23°C	8.0	10	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	290	--	°C	ISO 75-2/A
Melting Temperature ¹	295	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	4.0E-5	--	cm/cm/°C	

Transverse	6.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	> 1.0E+15	1.0E+10	ohms·cm	IEC 60093
Electric Strength	30	20	kV/mm	IEC 60243-1
Comparative Tracking Index	200	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
0.670 mm	V-0	--		
1.50 mm	V-0	--		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	280 to 320		°C	
Middle Temperature	300 to 320		°C	
Front Temperature	300 to 320		°C	
Nozzle Temperature	300 to 320		°C	
Processing (Melt) Temp	305 to 320		°C	
Mold Temperature	80.0 to 120		°C	
Injection Rate	Moderate-Fast			
Back Pressure	2.00 to 10.0		MPa	
Screw Compression Ratio	2.5:1.0			
NOTE				

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT