

NORYL™ APS430 resin

Polyphenylene Sulfide + PPE

SABIC Innovative Plastics Asia Pacific

Message:

NORYL™ APS430 resin is a Polyphenylene Sulfide + PPE (PPS+PPE) material. It is available in Asia Pacific. Primary attribute of NORYL™ APS430 resin: Flame Rated.

General Information			
UL YellowCard	E45587-100154477		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.30 to 0.70	%	Internal Method
Water Absorption (24 hr)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	123	MPa	Internal Method
Tensile Elongation (Break)	10	%	Internal Method
Flexural Modulus	8620	MPa	ASTM D790
Flexural Strength	167	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	78	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.20 mm)	255	°C	ASTM D648
CLTE - Flow (-30 to 30°C)	1.8E-5 to 5.8E-5	cm/cm/°C	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Dielectric Constant			ASTM D150
50 Hz	3.30		
60 Hz	3.30		
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT