

3M™ Dyneon™ Fluoroplastic PFA 6515NZ

Perfluoroalkoxy

3M Advanced Materials Division

Message:

3M™ Dyneon™ Fluoroplastic PFA 6515NZ (a fully fluorinated copolymer of tetrafluoroethylene and perfluorovinylether) has exceptional heat resistance, excellent electrical properties and excellent chemical and weather resistance.

Features

- Wide service temperature range
- Excellent, almost universal resistance to solvents and chemicals
- Extremely high weathering resistance and UV stability
- Excellent electrical properties
- High limiting oxygen index: Does not support combustion
- Smooth surfaces
- Good non-stick characteristics
- Good low-friction properties
- Improved adhesion to metal

General Information			
Features	Copolymer		
	Good Chemical Resistance		
	Good Electrical Properties		
	Good UV Resistance		
	Good Weather Resistance		
	High Heat Resistance		
	Low Friction		
	Non-Stick		
	Solvent Resistant		
Uses	Wire & Cable Applications		
Forms	Pellets		
Processing Method	Injection Molding		
	Wire & Cable Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	2.15	g/cm ³	ISO 12086
Melt Mass-Flow Rate (MFR) (372°C/5.0 kg)	15	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	60		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break, 23°C)	26.0	MPa	ISO 527-1
Tensile Strain (Break, 23°C)	420	%	ISO 527-1
Flexural Modulus	620	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	310	°C	ISO 12086

Flammability	Nominal Value	Unit	Test Method
Oxygen Index	> 95	%	ASTM D2863
Injection	Nominal Value	Unit	
Processing (Melt) Temp	250 to 400	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	< 400	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

