

Polipom 100 TF2

Acetal (POM) Copolymer

Poliblend S.p.a.

Message:

Polipom 100 TF2 is an Acetal (POM) Copolymer material. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America. Primary attribute of Polipom 100 TF2: Lubricated.

General Information			
Additive	PTFE Lubricant		
Features	Lubricated		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Density	1.46	g/cm ³	ISO 1183
Molding Shrinkage	1.8 to 2.2	%	
Water Absorption (23°C, 24 hr)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3100	MPa	ISO 527-2
Tensile Stress (Yield)	60.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	7.0	%	
Break	20	%	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	52	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	160	°C	ISO 75-2/B
1.8 MPa, Unannealed	105	°C	ISO 75-2/A
Continuous Use Temperature ¹	80.0	°C	
Vicat Softening Temperature	165	°C	ISO 306/A120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Melting Temperature	175	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	> 600	V	IEC 60112
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	> 3.0	hr	
Processing (Melt) Temp	180 to 200	°C	
Mold Temperature	70.0 to 90.0	°C	
NOTE			
1.	Without Load		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

