

SABIC® STAMAX 30YK270 resin

Polypropylene

SABIC Innovative Plastics

Message:

SABIC® STAMAX 30YK270 is a 30% long glass fiber reinforced polypropylene with improved impact and flow properties. The glass fibers are chemically coupled to the PP matrix, resulting in high stiffness and strength. The IMDS is 80929807.

General Information			
Filler / Reinforcement	Long glass fiber, 30% filler by weight		
Features	Rigidity, high		
	High strength		
	Chemical coupling		
	Impact resistance, good		
	Good liquidity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.13	g/cm ³	ASTM D792
--	1.12	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2/1
--	6200	MPa	ISO 527-2/1
80°C	4400	MPa	ISO 527-2/1
120°C	3600	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/1A/50
Fracture	98.0	MPa	ISO 527-2/1A/50
Fracture, 80°C	60.0	MPa	ISO 527-2/1A/50
Fracture, 120°C	43.0	MPa	ISO 527-2/1A/50
Tensile Strain (Break)	2.3	%	ISO 527-2/50
Flexural Modulus ¹			ISO 178
64.0mm span	5500	MPa	ISO 178
80°C, 64.0mm span	3600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C ²	24	kJ/m ²	ISO 179/1eA
23°C ³	21	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ⁴			ISO 179/1eU
-30°C	70	kJ/m ²	ISO 179/1eU
23°C	57	kJ/m ²	ISO 179/1eU

Instrumented Dart Impact			
23°C, Energy at Peak Load ⁵	5.70	J	ASTM D3763
23°C, energy to peak power ⁶	5.80	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁷ (1.8 MPa, Unannealed)	157	°C	ISO 75-2/A
Additional Information	Nominal Value	Unit	Test Method
Glass Fiber Content	30	%	ISO 3451
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	2.0	hr	
Rear Temperature	230 - 290	°C	
Middle Temperature	225 - 285	°C	
Front Temperature	220 - 280	°C	
Nozzle Temperature	220 - 280	°C	
Processing (Melt) Temp	220 - 280	°C	
Mold Temperature	20.0 - 80.0	°C	
Back Pressure	0.00 - 0.500	MPa	
Injection instructions			
Screw Speed: Lowest Possible			
NOTE			
1.	2.0 mm/min		
2.	80*10*4mm, Cut		
3.	80*10*4 mm, Cut		
4.	80*10*4mm, Cut		
5.	6.60 m/sec		
6.	6.6 m/sec		
7.	80*10*4mm, Cut		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT