

TECHNYL® A 205F BLACK 21 N

Polyamide 66
Solvay Engineering Plastics

Message:
TECHNYL® A 205F Black 21 N is an unreinforced polyamide 66 for injection moulding. It is available in black color.

General Information				
Features		Fast Molding Cycle		
		High Flow		
Uses		Connectors		
		Fasteners		
		Thin-walled Parts		
Agency Ratings		UU 453/2010/EC		
RoHS Compliance		RoHS Compliant		
Appearance		Black		
Processing Method		Injection Molding		
Part Marking Code (ISO 11469)		>PA66<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183/A
Molding Shrinkage				Internal Method
Across Flow	1.9	--	%	
Flow	1.9	--	%	
Water Absorption (23°C, 24 hr)	1.2	--	%	ISO 62
Molding Shrinkage Isotropy	1.00	--		Internal Method
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3200	1400	MPa	ISO 527-2/1A
Tensile Strength				
Yield	85.0	--	MPa	ASTM D638
Yield	85.0	50.0	MPa	ISO 527-2/1A
Break	60.0	40.0	MPa	ISO 527-2/1A
Tensile Strain				
Yield	4.0	10	%	ISO 527-2/1A
Break	25	--	%	ASTM D638
Flexural Modulus				
--	3350	--	MPa	ASTM D790
--	3000	1300	MPa	ISO 178
Flexural Strength				

--	125	--	MPa	ASTM D790
--	120	50.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break	No Break		ISO 179/1eU
Notched Izod Impact				
--	80	--	J/m	ASTM D256
23°C	5.0	8.0	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	75.0	--	°C	ISO 75-2/Af
Melting Temperature	263	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 85°C	7.0E-5	--	cm/cm/°C	
Transverse : 23 to 85°C	7.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	5.0E+14	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+13	ohms·cm	IEC 60093
Electric Strength	27	26	kV/mm	IEC 60243-1
Relative Permittivity	2.90	3.20		IEC 60250
Dissipation Factor	0.030	0.080		IEC 60250
Comparative Tracking Index				IEC 60112
Solution A	600	600	V	
Solution B	550	--	V	
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.400 mm	V-2	--		
0.800 mm	V-2	--		
1.60 mm	V-2	--		
Glow Wire Flammability Index (1.60 mm)	850	--	°C	IEC 60695-2-12
Oxygen Index	29	--	%	ISO 4589-2
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	265 to 275		°C	
Middle Temperature	270 to 280		°C	
Front Temperature	280 to 290		°C	
Mold Temperature	60.0 to 80.0		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

