

Tecnoflon® PL 855

Fluoroelastomer
Solvay Specialty Polymers

Message:

TECNOFロン® PL 855 is a new generation low temperature peroxide curable medium viscosity fluoroelastomer with 64% wt fluorine content. Tecnoflon® PL 855 exhibits excellent low temperature flexibility (TR10 = -30°C). Like all other Tecnoflon® peroxide curable grades, it exhibits excellent processability; moreover it needs very short post-curing cycles.

Some of the basic properties of Tecnoflon® PL 855 are:

- Excellent low temperature flexibility
- Low post cure
- Superior mold flow
- Lack of mold fouling
- Excellent mold release

Tecnoflon® PL 855 can be used for injection, injection-compression and transfer molding of O-rings, gaskets and seals. Tecnoflon® PL 855 can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers.

This material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting. Finished goods may be produced by a variety of rubber processing methods.

General Information	
Features	Fast Cure
	Good Flow
	Good Mold Release
	Good Processability
	Low Temperature Flexibility
	Medium Viscosity
Uses	Belts/Belt Repair
	Blending
	Gaskets
	Hose
	Low Temperature Applications
	Profiles
	Seals
	Sheet
Appearance	Translucent
Forms	Slab
Processing Method	Calendering
	Compounding
	Compression Molding
	Extrusion
	Injection Molding
	Resin Transfer Molding

Physical	Nominal Value	Unit
Mooney Viscosity ¹ (ML 1+10, 121°C)	54	MU
Fluorine Content ²	64	%
NOTE		
1.	Raw polymer	
2.	Raw polymer	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

