

# Therma-Tech™ X TT9200-8708 EC

Polyphenylene Sulfide

PolyOne Corporation

## Message:

Therma-Tech™ Thermal Management Compounds have been engineered to combine the heat transfer and cooling capabilities of metals with the design freedom, weight reduction and cost advantages of thermoplastics. These materials provide the benefits of proprietary conductive additive technologies and the performance of select engineering thermoplastic resins. Therma-Tech compounds have been shown to improve thermal conductivity up to 100-times that of conventional plastics and can be used in a wide range of thermal management applications.

General Information			
Features	Electrically Conductive		
	Thermally Conductive		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.74	g/cm <sup>3</sup>	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup> (3.20 mm)	27600	MPa	ASTM D638
Tensile Strength <sup>2</sup> (3.20 mm)	55.2	MPa	ASTM D638
Tensile Elongation <sup>3</sup> (Break, 3.20 mm)	0.40	%	ASTM D638
Flexural Modulus (3.20 mm)	22100	MPa	ASTM D790
Flexural Strength (3.20 mm)	82.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	27	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Thermal Conductivity			ASTM E1461
-- <sup>4</sup>	4.0 to 5.0	W/m/K	
-- <sup>5</sup>	18 to 20	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 9.0E+3	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		Internal Method
Injection	Nominal Value	Unit	
Drying Temperature	140 to 150	°C	
Drying Time	4.0 to 6.0	hr	
Processing (Melt) Temp	320 to 340	°C	
Mold Temperature	140 to 160	°C	
NOTE			

1.	5.0 mm/min
2.	5.0 mm/min
3.	5.0 mm/min
4.	Through-Plane
5.	In-Plane

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

