

Miflon® 3123

Polytetrafluoroethylene

Jiangsu Meilan Chemical Co., Ltd.

Message:

Suspension PTFE Resin (Virgin Granular) (PTFE)

Quality Standard: Q/321200GDH014-2012

Reference Standard: HG/T2902-1997

Cleanness

Clean and white surface, well-distribution, no impurity

D=57mm, no color difference for rod cross section

General Information		
Features	Clean/High Purity	
Forms	Granules	
Physical	Nominal Value	Unit
Specific Gravity	2.12 to 2.17	g/cm ³
Moisture Content	< 0.040	%
Thermal Instability Index	< 50.0	
Mechanical	Nominal Value	Unit
Tensile Strength	> 25.5	MPa
Tensile Elongation (Break)	> 250	%
Thermal	Nominal Value	Unit
Melting Temperature	322 to 332	°C
Electrical	Nominal Value	Unit
Dielectric Strength	> 60	kV/mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT