

Iupilon® ECF2015R

Polycarbonate

Mitsubishi Engineering-Plastics Corp

Message:

Iupilon® ECF2015R is a Polycarbonate (PC) material filled with 15% carbon fiber. It is available in Asia Pacific, Europe, or North America for injection molding.

Important attributes of Iupilon® ECF2015R are:

Flame Rated

Flame Retardant

General Information			
Filler / Reinforcement	Carbon Fiber, 15% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.26	g/cm ³	ISO 1183
Molding Shrinkage			
Across Flow : 3.20 mm	0.20 to 0.40	%	
Flow : 3.20 mm	0.050 to 0.25	%	
Water Absorption (Saturation, 23°C)	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11500	MPa	ISO 527-2
Tensile Stress (Break)	130	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	9600	MPa	ISO 178
Flexural Stress	180	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	50	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	150	°C	ISO 75-2/B
1.8 MPa, Unannealed	146	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.800 mm	V-2		
1.50 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	

Drying Time	4.0 to 8.0	hr
Rear Temperature	270 to 290	°C
Middle Temperature	280 to 300	°C
Front Temperature	280 to 300	°C
Nozzle Temperature	280 to 300	°C
Mold Temperature	80.0 to 120	°C
Injection Pressure	50.0 to 150	MPa
Screw Speed	50 to 100	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

