

KumhoSunny PET HEG3630

Polyethylene Terephthalate
Shanghai KumhoSunny Plastics Co., Ltd.

Message:
HEG3630 is a 30% glass fiber reinforced, modified polyethylene terephthalate for injection molding. offering high rigidity,high heat resistance, good surface quality and dimensional stability.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Fatigue Resistant		
	Good Dimensional Stability		
	Good UV Resistance		
	High Heat Resistance		
	High Rigidity		
Uses	Automotive Applications		
	Automotive Interior Parts		
	Electrical Parts		
	Electrical/Electronic Applications		
	Household Goods		
UL File Number	E254819		
	E65424		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.60	g/cm ³	ASTM D792
--	1.58	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (265°C/2.16 kg)	30	g/10 min	ISO 1133
Molding Shrinkage			
Flow	0.40 to 0.80	%	ASTM D955
--	0.60 to 1.0	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
--	150	MPa	ASTM D638
--	130	MPa	ISO 527-2/5
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus			

--	11000	MPa	ASTM D790
-- ¹	8500	MPa	ISO 178
Flexural Strength			
--	250	MPa	ASTM D790
-- ²	200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	5.0	kJ/m ²	
23°C	7.5	kJ/m ²	
Notched Izod Impact			
3.20 mm	100	J/m	ASTM D256
23°C	7.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	253	°C	ASTM D648
1.8 MPa, Unannealed	230	°C	ASTM D648
1.8 MPa, Unannealed ³	225	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120 to 140	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	< 0.020	%	
Rear Temperature	245 to 260	°C	
Middle Temperature	250 to 265	°C	
Front Temperature	255 to 270	°C	
Nozzle Temperature	260 to 275	°C	
Processing (Melt) Temp	245 to 275	°C	
Mold Temperature	100 to 120	°C	
Back Pressure	0.200 to 0.800	MPa	
Screw Speed	20 to 100	rpm	
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		
3.	120°C/h		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

