

Cri-Line TFEP-920

Fluoroelastomer

Cri-Tech, Inc.

Message:

55% Fluorine copolymers of tetrafluoroethylene and propylene. TFEP compounds exhibit outstanding resistance to hot water, steam, acids and alkalis. These compounds also give superior performance in amines and phosphate esters as compared to conventional fluoroelastomers.

General Information		
Features	Acid Resistant	
	Alkali Resistant	
	Copolymer	
	Steam Resistant	
Physical	Nominal Value	Unit
Specific Gravity	1.60	g/cm ³
Mooney Viscosity (ML 1+10, 121°C)	150	MU
Fluorine Content	55	%
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A)	87	
Elastomers	Nominal Value	Unit
Tensile Stress (100% Strain)	13.0	MPa
Tensile Strength	13.9	MPa
Tensile Elongation (Break)	110	%
Compression Set ¹ (200°C, 22 hr)	40	%
NOTE		
1.	Plied discs	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT