

Arnite® TZ6 280

Polybutylene Terephthalate

DSM Engineering Plastics

Message:

Arnite® TZ6 280 is a Polybutylene Terephthalate (PBT) material filled with 20% glass bead and 20% glass fiber. It is available in Asia Pacific or North America. Primary attribute of Arnite® TZ6 280: Flame Rated.

General Information			
Filler / Reinforcement	Glass Bead,20% Filler by Weight		
	Glass Fiber,20% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Density	1.60	g/cm ³	ISO 1183
Water Absorption			ISO 62
Saturation, 23°C	0.25	%	
Equilibrium, 23°C, 50% RH	0.15	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8700	MPa	ISO 527-2
Tensile Stress (Break)	100	MPa	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	40	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	210	°C	ISO 75-2/B
1.8 MPa, Unannealed	195	°C	ISO 75-2/A
Melting Temperature ¹	225	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	4.0E-5	cm/cm/°C	
Transverse	7.5E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.800 mm	HB		
1.60 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	3.0 to 12	hr	

Rear Temperature	230 to 240	°C
Middle Temperature	230 to 250	°C
Front Temperature	240 to 260	°C
Nozzle Temperature	240 to 260	°C
Processing (Melt) Temp	240 to 270	°C
Mold Temperature	60.0 to 100	°C
Injection Rate	Moderate-Fast	
Back Pressure	3.00 to 10.0	MPa
Screw Compression Ratio	2.5:1.0	
NOTE		

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

