

QR Resin QR-1018

Polycarbonate

QTR, Inc.

Message:

Available with UV (V) or Release (R).

General Information			
Features	High Impact Resistance		
Appearance	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	61.4	MPa	ASTM D638
Flexural Modulus	2340	MPa	ASTM D790
Flexural Strength (Yield)	89.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	640	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	138	°C	
1.8 MPa, Unannealed	132	°C	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	2.0 to 4.0	hr	
Drying Time, Maximum	4.0	hr	
Rear Temperature	260 to 282	°C	
Middle Temperature	271 to 293	°C	
Front Temperature	282 to 293	°C	
Nozzle Temperature	277 to 293	°C	
Processing (Melt) Temp	282 to 304	°C	
Mold Temperature	71.1 to 93.3	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT