

Moplen HP521M

Polypropylene Homopolymer

PolyMirae

Message:

Moplen HP521M is a polypropylene homopolymer manufactured using the Spheripol process. Potential applications include general purpose and metallizable CPP, as well as food and clothes packaging.

| General Information | | | |
|--|-------------------|-------------------|-------------|
| Features | Rigid, good | | |
| | Homopolymer | | |
| | Workability, good | | |
| | General | | |
| Uses | Packaging | | |
| | Laminate | | |
| | Bags | | |
| | cast film | | |
| | Food packaging | | |
| | General | | |
| Forms | Particle | | |
| Processing Method | cast film | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.900 | g/cm ³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 8.0 | g/10 min | ASTM D1238 |
| Hardness | Nominal Value | Unit | Test Method |
| Rockwell Hardness (R-Scale) | 100 | | ASTM D785 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 35.3 | MPa | ASTM D638 |
| Tensile Elongation (Yield) | 12 | % | ASTM D638 |
| Flexural Modulus | 1570 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 29 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (0.45 MPa, Unannealed) | 110 | °C | ASTM D648 |
| Vicat Softening Temperature | 155 | °C | ASTM D1525 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT